



Grade	SFC-550B
Product	Polypropylene, Random Compolymer

General Information

Key Features

- Good processability, excellent clarity and gloss
- Slip additive free

Applications

- General CPP Film
- Food Packaging Film(Semi-Retort CPP)

Item	Measuring Method	Unit	Value
Physical Properties			
Melt Flow Index (230°C, 2.16kg)	ASTM D1238	g/10min	8.0
Density	ASTM D792	g/cm ³	0.9
Mechanical Properties			
Tensile Stress (Yield)	ASTM D638	kgf/cm ²	270
Tensile Strain (Break)	ASTM D638	%	>500
Flexural Modulus	ASTM D790	kgf/cm ²	10000
Rockwell Hardness	ASTM D785	R	85
Impact Properties			
Izod Impact Strength (notched, 23°C)	ASTM D256	kgf·cm/cm	3.7
Thermal Properties			
Melting Temperature	LC Method	°C	148
Heat Deflection Temperature (4.6kgf/cm ²)	ASTM D648	°C	80
Film Properties			
Haze	ASTM D1003	%	<1.5
Coefficient of Friction	ASTM D1894		<0.8
Heat Seal Temperature	LC Method	°C	132

1. Physical Properties : these are not to be construed as specifications
2. Measured on 30 μ m mono-layer CPP film made of LOTTE CHEMICAL's cast film grade
3. ISO 9001, 14001, /TS 16949

* The last update date : 2023/01/01