

云天化® M120

Acetal (POM) Copolymer



云南云天化股份有限公司
YUNNAN YUNTIANHUA CO., LTD

General

Material Status	• Similar to M90, but with higher flow		
Features	• Acid Resistant	• Good Abrasion Resistance	• High Hardness
	• Bacteria Resistant	• Good Chemical Resistance	• High Stiffness
	• Base Resistant	• Good Dimensional Stability	• Low Friction
	• Copolymer	• Good Electrical Properties	• Low Warpage
	• Fatigue Resistant	• Good Flow	• Solvent Resistant
Uses	• Automotive Electronics	• Fittings	• Thin-walled Parts
	• Automotive Exterior Parts	• Gears	• Valves/Valve Parts
	• Aumomotive Under the Hood	• pining	• Wheels
Forms	• Pellets		
Processing Method	• Injection Molding		

Physical properties	Value	Unit	Test Standard
Density	1.41	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR) (190°C/2.16Kg)	13	g/10min	ISO 1133
Water Absorption (24 h, 23°C,50%RH)	0.12	%	ISO 62
Mechanical properties	Value	Unit	Test Standard
Tensile Stress at yield	63	MPa	ISO 527-2
Tensile modulus	2650	MPa	ISO 527-2
Strain at break	35	%	ISO 527-2
Flexural strength	88	MPa	ISO 178
Flexural modulus	2500	MPa	ISO 178
Charpy notched impact strength	6.5	KJ/m ²	ISO 179/1eA
Thermal properties	Value	Unit	Test Standard
Heat Deflection Temperature 1.8MPa, Unannealed	95	°C	ISO 75
Other	Value	Unit	Test Standard
Molding Shrinkage	2.0	%	YUNTIANHUA
Flammability properties	Value	Unit	Test Standard
Flame Rating-UL	HB	class	UL94

Notes to users

Values shown are based on testing of laboratory test specimens and represent data that fall within the standard range of properties for natural material. These values alone do not represent a sufficient basis for any part design and are not intended for use in establishing maximum, minimum, or ranges of values for specification purposes. Colorants or other additives may cause significant variations in data values.



Recommended Injection Molding Conditions

- Material Drying : 80 – 90°C, 3-4 hours

- Cylinder Temperature:

Nozzle : 180 - 210 (°C)

Front Section : 190 – 210 (°C)

Center Section : 170 – 200 (°C)

Rear Section : 160 – 180 (°C)

- Melt Temperature : 180 – 210 (°C)

- Mold Temperature : 60 – 90 (°C)

(Precision parts are often molded at mold temperature as high as 120°C)

- Pressure :

Injection Pressure : 50 – 100 MPa

Holding Pressure : 30 – 80 MPa

Back Pressure: 0 – 0.5 MPa

- Screw Rotational Speed : 50 – 120 rpm

Acquired Certifications of Yuntianhua POM

- RoHS test

- PFOS test

- Halogen element test

- SVHC test

- DMF test

- EN1186btest

- DBT&TBT test

- EN71-3 test

- Certification W18 test

- Certification FDA

- Certification UL

- Certification NSF

Contact information

• Production

YunNan YunTianHua CO., LTD

<http://www.yyth.com.cn>

Headquarters: YunNan • ShuiFu

Tel: 0870-8662003

Fax: 0870-8636337

Branch: ChongQing • ChangShou

Tel: 023-40717299

Fax: 023-68980888

• Technical Support

Technical support hotline: 400-1188-668