

TECHNICAL DATA SHEET

TECHNYL 4EARTH A2E 219 V30 BK
(Previously ECONAMID PLUS 66G30H1 BK)

Polyamide 66, 30% glass fiber reinforced, heat-aging stabilized, for injection moulding, black

General

Feature	Heat-aging stabilized
Polymer type	PA66 (Polyamide 66)
Processing technology	Injection molding
Certification	RoHS

Product identification

ISO 1043 abbreviation	PA66-GF30
ISO 16396 designation	PA66,GF30(R>50),M1H,S14-080

	Condition	Standard	Unit	Value
Physical properties				
Density		ISO 1183	g/cm ³	1.35

Mechanical properties

				dam / cond.*
Tensile modulus	1 mm/min	ISO 527-1/-2	MPa	8500 / 5400
Stress at break	5 mm/min	ISO 527-1/-2	MPa	130 / 85
Strain at break	5 mm/min	ISO 527-1/-2	%	2.5 / 5
Charpy impact strength, +23°C	+23°C	ISO 179/1eU	kJ/m ²	35 / 50
Charpy notched impact strength, +23°C	+23°C	ISO 179/1eA	kJ/m ²	6.5 / 11
Izod impact strength, +23°C	+23°C	ISO 180/1U	kJ/m ²	30 / 45
Izod notched impact strength, +23°C	+23°C	ISO 180/1A	kJ/m ²	6 / 10

Thermal properties

Melting temperature, 10°C/min		ISO 11357-1	°C	262
Temp. of deflection under load, 0.45 MPa	0.45 MPa	ISO 75	°C	255
Temp. of deflection under load, 1.80 MPa	1.80 MPa	ISO 75	°C	245
Vicat softening temperature	50°C/h - 50N	ISO 306	°C	250

TECHNICAL DATA SHEET

TECHNYL 4EARTH A2E 219 V30 BK

	Condition	Standard	Unit	Value
Electrical properties				
Volume resistivity		IEC 62631-3-1	ohm.m	1E+013
Surface resistivity		IEC 62631-3-1	ohm	1E+013

Burning behaviour

Flammability, 0.75 mm	0.75 mm	UL 94		HB
Burning rate, FMVSS, Thickness 1 mm		FMVSS 302		< 100 mm/min

*Test run at 23°C if not differently specified, DAM state (dry as moulded), valid for black products.
: conditioned according to ISO 1110

Processing conditions

Drying temperature/time	75-85°C / 2-4h (with dew point of dried air < -30 °C)			
Recommended melt temperature	270 - 290 °C			
Recommended mould temperature	90 - 110 °C			

These parameters are typical of the product but should be related to the type of machinery used and to the type of moulded part. These TECHNYL grades are not recommended for injection moulding hot runner systems with a diameter below 1mm.

Disclaimer

The information provided in this documentation corresponds to our technical knowledge at the date of its publication and do not constitute a specification. This information may be subject to revision at our discretion. Domo cannot anticipate all conditions under which this information and our products of other manufactures in combination with our products may be used. Domo accepts no responsibility for results obtained by the application of this information or for the safety and suitability of our products alone or in combination with other products. Users are advised to make their own tests to determine the safety and suitability of each product or product combination for their own purposes. Unless otherwise agreed in writing, Domo sells the product without warranties. Buyers and users assume all responsibility and liability for loss or damage arising from handling and use of our products, whether used alone or in combination with other products. Unless specifically indicated, the grades mentioned are not suitable for applications in the pharmaceutical/medical sector.