

TECHNICAL DATA SHEET

TECHNYL C 116 BK

(Previously DOMAMID 6LV 100)

Polyamide 6, improved flowability, for injection moulding

General

| | | |
|-----------------------|------------------------------|----------------|
| Feature | Improved flowability | |
| Polymer type | PA6 (Polyamide 6) | |
| Processing technology | Injection molding | |
| Certification | RoHS EC 1907/2006 (REACH) | UL-Yellow Card |
| Colors available | Black Red | Grey |
| Forms | Pellets | |

Product identification

| | |
|-----------------------|----------------|
| ISO 1043 abbreviation | PA6 |
| ISO 16396 designation | PA6,M1,S12-030 |

| Condition | Standard | Unit | Value |
|-----------|----------|------|-------|
|-----------|----------|------|-------|

Physical properties

| | Condition | Standard | Unit | Value |
|-----------------------------|-----------|-----------------|--------------------|-----------|
| Density | | ISO 1183 | g/cm ³ | 1.13 |
| Molding shrinkage, parallel | | ISO 294-4, 2577 | % | 0.9 - 1.1 |
| Molding shrinkage, normal | | ISO 294-4, 2577 | % | 1.1 - 1.3 |
| Viscosity number | 96% H2SO4 | ISO 307 | cm ³ /g | 135 |

Mechanical properties

dam / cond.*

| | Condition | Standard | Unit | Value |
|---------------------------------------|-----------|--------------|-------------------|----------|
| Tensile modulus | 1 mm/min | ISO 527-1/-2 | MPa | 2900 / - |
| Strain at break | 50 mm/min | ISO 527-1/-2 | % | 50 / - |
| Yield stress | 50 mm/min | ISO 527-1/-2 | MPa | 78 / - |
| Flexural modulus, ISO 178 | 2 mm/min | ISO 178 | MPa | 2600 / - |
| Flexural strength, ISO 178 | 2 mm/min | ISO 178 | MPa | 100 / - |
| Charpy impact strength, +23°C | +23°C | ISO 179/1eU | kJ/m ² | NB / - |
| Charpy notched impact strength, +23°C | +23°C | ISO 179/1eA | kJ/m ² | 5 / - |
| Izod impact strength, +23°C | +23°C | ISO 180/1U | kJ/m ² | NB / - |
| Izod notched impact strength, +23°C | +23°C | ISO 180/1A | kJ/m ² | 5 / - |

| Condition | Standard | Unit | Value |
|-----------|----------|------|-------|
|-----------|----------|------|-------|


Thermal properties

| | | | | |
|-------------------------------|--|-------------|----|-----|
| Melting temperature, 10°C/min | | ISO 11357-1 | °C | 221 |
|-------------------------------|--|-------------|----|-----|

Electrical properties

| | | | | |
|---------------------|--|---------------|-------|--------|
| Volume resistivity | | IEC 62631-3-1 | ohm.m | 1E+013 |
| Surface resistivity | | IEC 62631-3-1 | ohm | 1E+013 |

Burning behaviour

| | | | | |
|---|---|-----------|--|--------------|
| UL Yellow Card availability  | Click here to have access to the UL Yellow Card → E170540-100053880 | | | |
| Flammability, 0.75 mm | 0.75 mm | UL 94 | | V2 |
| Flammability, 1.5 mm | 1.5 mm | UL 94 | | V2 |
| Flammability, 3.0 mm | 3.0 mm | UL 94 | | V2 |
| Burning rate, FMVSS, Thickness 1 mm | | FMVSS 302 | | < 100 mm/min |

Test run at 23°C if not differently specified, DAM state (dry as moulded), valid for natural colored products.
 *: conditioned according to ISO 1110

Processing conditions

| | |
|-------------------------------|--------------|
| Drying temperature/time | 80°C |
| Suggested max moisture | 0.2 % |
| Rear temperature | 230 - 235 °C |
| Middle temperature | 235 - 240 °C |
| Front temperature | 235 - 245 °C |
| Recommended melt temperature | 230 - 245 °C |
| Recommended mould temperature | 60 - 80 °C |

These parameters are typical of the product but should be related to the type of machinery used and to the type of moulded part.

Injection notes

The material is supplied in airtight bags, ready for use. In case that the virgin material has absorbed moisture, it must be dried with a dehumidified air drying equipment, dew point minimum -20°C. Recommended time 2-4h.

Injection advice

For unfilled polyamides, Domo recommends the use of high alloy steel with a low chromium content. For example: X38CrMoV5-1 (EN Norm) - 1.2367 /1.2343 (DIN Norm). In the case of high requirements on surface quality a mould temperature of up to 120°C can be considered. The processing parameters like processing temperatures are a recommendation and can be adjusted in function of injection machine size, part geometry / design.

Disclaimer

The information provided in this documentation corresponds to our technical knowledge at the date of its publication and do not constitute a specification. This information may be subject to revision at our discretion. Domo cannot anticipate all conditions under which this information and our products of other manufactures in combination with our products may be used. Domo accepts no responsibility for results obtained by the application of this information or for the safety and suitability of our products alone or in combination with other products. Users are advised to make their own tests to determine the safety and suitability of each product or product combination for their own purposes. Unless otherwise agreed in writing, Domo sells the product without warranties. Buyers and users assume all responsibility and liability for loss or damage arising from handling and use of our products, whether used alone or in combination with other products. Unless specifically indicated, the grades mentioned are not suitable for applications in the pharmaceutical/medical sector.