


**ERACLENE®
SB 60 BA**

 HDPE
High density polyethylene bio attributed

SUSTAINABILITY

The product Eraclene SB 60 BA 'Bio attributed' is a highly sustainable HDPE produced using bionafra from renewable raw materials together with traditional raw materials. In order to attribute the sustainable feedstock component to the final product Versalis applies the Mass Balance approach, a recognized methodology that allows to trace the flow of materials along the value chain and to assign the sustainability characteristic of the raw material to the final product on a documentary basis. Eraclene SB 60 BA provides the same chemical composition and physical-mechanical performance of the traditional grade, in addition is accompanied by a sustainability declaration that certifies the share of bio attributed product. It is a high-density polyethylene with medium-high molecular weight, hexene copolymer, obtained with the gas phase, suitable for extrusion. The production of Eraclene SB 60 BA allows to contribute to the circular economy, since the bionafra used derives from renewable resources (e.g. vegetable oils). Eraclene SB 60 BA will be bio attributed for 95%. The exact amount of 'bio attributed' product will be reported in the sustainability certificate issued upon the delivery of the product.

MAIN PROPERTIES

| Resin Properties | Value | Unit | Test method |
|---------------------------------|-------|-------------------|----------------|
| Melt Flow Rate (190 °C/2.16 kg) | - | g/10min | ISO 1133 |
| Melt Flow Rate (190 °C/5 kg) | 0.4 | g/10min | ISO 1133 |
| Melt Flow Rate (190 °C/21.6 kg) | 10 | g/10min | ISO 1133 |
| Density | 0.948 | g/cm ³ | ISO 1183 |
| Melting Point | 130 | °C | Metodo interno |
| Brittleness temperature | <- 60 | °C | ASTM D 746 |
| Vicat softening point (1 kg) | 125 | °C | ISO 306/A |

| Mechanical Properties * | Value | Unit | Test method |
|---|-------|------|----------------|
| Tensile stress at yield | 22 | MPa | ISO 527 |
| Tensile stress at break | 31 | MPa | ISO 527 |
| Tensile strain at yield | - | % | ISO 527 |
| Elongation at break | >800 | % | ISO 527 |
| Flexural modulus | 900 | MPa | ISO 178 |
| Hardness Shore D | 61 | - | ISO 868 A |
| Falling weight | - | J | ISO 6603-2 |
| Izod impact strength, notched | 260 | J/m | ASTM D 256 |
| Environmental Stress Cracking Resistance (ESCR) | - | h | ASTM D 1693(B) |

(*) Values are referred to compression moulded specimens. Actual properties are typical and may vary depending upon operating conditions.



ERACLENE® HDPE / High density polyethylene bio attributed

SB 60 BA

MAIN APPLICATIONS

Eraclene SB 60 BA is recommended for the production of extruded sheets to be used as semi finished items for thermoforming and protection profiles for metallic parts. The excellent wear resistance properties and low friction allow Eraclene SB 60 BA to be used for the preparation of technical products. Thanks to high noise absorption, the sheets produced by Eraclene SB 60 BA can be used as acoustic insulator for barrier construction.

PROCESSING NOTES

Eraclene SB 60 BA can be easily extruded. Due to its high flowability (low viscosity at high shear rates), Eraclene SB 60 BA exhibits low energy consumption and good extrusion output. The recommended temperature profile is between 200 °C and 230 °C.

STORAGE AND HANDLING

Eraclene SB 60 BA is supplied in pellet form. This material may readily be conveyed and bulk fed through equipment designed for conventional pelletized polyethylene resin, provided the equipment is designed to prevent accumulation of the fines and dust particles that are contained in all polyethylene resins. These fines and dust particles can, under certain conditions, pose an explosion hazard. We recommend that the conveying system used be equipped with filters of adequate size, operated and maintained in such a manner to ensure that no leaks develop and earthed adequately. We further recommend that good housekeeping should be practiced throughout your facility. The product should be stored in dry conditions at temperatures below 50°C and protected from sunlight. Improper storage can initiate degradation which results in odor generation, color changes and can have negative effects on the physical properties of the product. Before using this product, it is recommended to read and understand the relevant Safety Data Sheet.

AVAILABILITY

Contact the Versalis sales office nearest to you regarding availability and your specific application requirements.

FOOD CONTACT STATUS

Eraclene SB 60 BA complies with the rules and regulations of the European Union, as well as other countries, regarding the use of plastic materials in food contact applications. Certificates of compliance are available upon request.

TECHNICAL MANAGEMENT POLYETHYLENE

Center and South Europe and Americas

Versalis S.p.A.

Head Office
Piazza Boldrini, 1
20097 San Donato Milanese (MI) - Italy
tel. +39 0252032998 + 39 0252042262
tel. +39 0252042005 + 39 0252032072
+39 0252042984

Mantova
Via Taliercio 14 - 46100 Mantova (MN) - Italy
tel. +39 0376305520 / +39 0376305620

North Europe and ROW

Versalis S.p.A.

4531 Route des Dunes - CS 20060 Mardyck 59279
Dunkerque - France
tel. +33 328235516 / +33 328235512

Duesseldorfer Str. 13
65760 Eschborn - Deutschland
tel +49 15140260561

IMPORTANT: please consult the relevant safety data sheet for more detailed information. The information and data presented herein are to the best of our knowledge true and accurate but no warranty or guarantee, expressed or implied, is made nor is any liability accepted with respect to the use of such information and data. Versalis is available to provide the guaranteed values for each product on demand

DISCLAIMER: it is the sole responsibility of the end-user to determine the safety, the regulatory compliance as well as the technical suitability of the product for the intended application. The product is not intended for use in medical devices and pharmaceutical applications; Versalis declines all responsibility and cannot be held liable in case of use in the above-mentioned applications.