

B 755

Technical Data Sheet

SAN

Kostil® B 755 is a Styrene-Acrylonitrile copolymer with a good chemical resistance and a very low residual monomer content.

This easy flow grade exhibits a high clarity and is designed for compounding.

Designation: Thermoplastic ISO 4894-SAN 2,MRS,105-25

Applications

Kostil® B 755 is suitable for:

- compound

Typical processing data

Injection moulding:

- predrying 1 - 2 hrs at 80°C in circulated air oven
- melt temperature 190 - 250 °C
- mould temperature 40 - 75°C

Certification

✓ UL 94 ✓ NSF 51

Kostil® B 755, as supplied in the original packaging, by composition is compliant to some existing regulations on plastic materials intended for food contact.

Storage

- ⚠ Store away from atmospheric agents and direct sunlight, away from sources of heat and light.
- 🕒 The product, if stored correctly, keeps its characteristics for at least fifteen months.

General information

Kostil® B 755 is available in natural shades, code 2000.

For further information, please contact Versalis directly writing to info.styrenics@versalis.eni.com .

B 755

SAN

Technical Data Sheet

Property	Test Conditions	Test method	Units	Values
General				
Water absorption	24h - 23°C	ISO 62	%	< 0,2
Density	-	ISO 1183	g/cm ³	1,07
Bulk density	-	ISO 60	g/cm ³	0,65
Rheological				
Melt flow rate	220°C - 5kg	ISO 1133	g/10'	21
Melt flow rate	220°C - 10kg	ISO 1133	g/10'	70
Mechanical				
Tensile strain at break	5 mm/min	ISO 527	%	1,7
Tensile stress at break	5 mm/min	ISO 527	MPa	54
Rockwell hardness	L/M	ISO 2039/2	-	M 83
Tensile modulus	1 mm/min	ISO 527	MPa	3500
Thermal				
Coefficient of linear thermal expansion	-	ISO 11359-2	10 ⁻⁵ /°C	7
Moulding shrinkage	-	ISO 294/4	%	0,4 ÷ 0,6
Deflection temperature under load (annealed)	1,82 MPa - 120°C/h	ISO 75 A	°C	97
Vicat softening temperature	50 N - 50°C/h	ISO 306/B	°C	104
Vicat softening temperature	10 N - 50°C/h	ISO 306/A	°C	107
Flammability				
Flame behaviour	1,5 mm	UL 94	cl.	HB

Please consult the relevant safety data sheet for more detailed information.

The information and data presented herein are to the best of our knowledge true and accurate but no warranty or guarantee, expressed or implied, is made nor is any liability accepted.

Versalis is available to provide the guaranteed values for each product on demand.