



# ERACLENE® MQ 70 U BA

HDPE  
High density polyethylene bio attributed



## SUSTAINABILITY

The product Eraclene MQ 70 U BA 'Bio attributed' is a highly sustainable HDPE produced using bionafra from renewable raw materials together with traditional raw materials. In order to attribute the sustainable feedstock component to the final product Versalis applies the Mass Balance approach, a recognized methodology that allows to trace the flow of materials along the value chain and to assign the sustainability characteristic of the raw material to the final product on a documentary basis. Eraclene MQ 70 U BA provides the same chemical composition and physical-mechanical performance of the traditional grade, in addition is accompanied by a sustainability declaration that certifies the share of bio attributed product. It is a gas phase high density polyethylene resin (HDPE) with antioxidants, suitable for injection moulding application. The production of Eraclene MQ 70 U BA allows to contribute to the circular economy, since the bionafra used derives from renewable resources (e.g. vegetable oils). Eraclene MQ 70 U BA will be bio attributed for a 95%. The exact amount of "bio attributed" product will be reported in the sustainability certificate issued upon the delivery of the product. Eraclene MQ 70 U BA will be bio attributed for 95%. The exact amount of "bio attributed" product will be reported in the sustainability certificate issued upon the delivery of the product.

## MAIN PROPERTIES

Resin Properties	Value	Unit	Test method
Melt Flow Rate (190 °C/2.16 kg)	11	g/10min	ISO 1133
Melt Flow Rate (190 °C/5 kg)	-	g/10min	ISO 1133
Melt Flow Rate (190 °C/21.6 kg)	-	g/10min	ISO 1133
Density	0.952	g/cm <sup>3</sup>	ISO 1183
Melting Point	131	°C	Metodo interno
Brittleness temperature	<- 60	°C	ASTM D 746
Vicat softening point (1 kg)	125	°C	ISO 306/A
Mechanical Properties *	Value	Unit	Test method
Tensile stress at yield	25	MPa	ISO 527
Tensile stress at break	15	MPa	ISO 527
Tensile strain at yield	-	%	ISO 527
Elongation at break	300	%	ISO 527
Flexural modulus	1250	MPa	ISO 178
Hardness Shore D	65	-	ISO 868 A
Falling weight	-	J	ISO 6603-2
Izod impact strength, notched	65	J/m	ASTM D 256
Environmental Stress Cracking Resistance (ESCR)	-	h	ASTM D 1693(B)

(\*) Values are referred to compression moulded specimens. Actual properties are typical and may vary depending upon operating conditions.

## MAIN APPLICATIONS

Eraclene MQ 70 U BA is specifically designed to produce items with good mechanical properties: light-weight crates, houseware. For its flowability, the resin can be used whenever high production rate is a key issue. The polymer produced has an excellent thermal stability during the transformation phase.

## PROCESSING NOTES

Eraclene MQ 70 U BA is readily processable by conventional injection moulding equipment with excellent results.

Typical processing conditions (\*)

Temperature profile of the barrel (°C) 190 - 260

Temperature of the mould (°C) 10 - 40

(\*) Processing conditions are depending on several parameters: the shape of the part to be manufactured, the localisation of the injection point, the injection moulding machine and the cooling of the mould.

## STORAGE AND HANDLING

Eraclene MQ 70 U BA is supplied in pellet form. This material may readily be conveyed and bulk fed through equipment designed for conventional pelletized polyethylene resin, provided the equipment is designed to prevent accumulation of the fines and dust particles that are contained in all polyethylene resins. These fines and dust particles can, under certain conditions, pose an explosion hazard. We recommend that the conveying system used be equipped with filters of adequate size, operated and maintained in such a manner to ensure that no leaks develop and earthed adequately. We further recommend that good housekeeping should be practiced throughout your facility.

The product should be stored in dry conditions at temperatures below 50°C and protected from sunlight. Improper storage can initiate degradation which results in odor generation, color changes and can have negative effects on the physical properties of the product. Before using this product, it is recommended to read and understand the relevant Safety Data Sheet.

## AVAILABILITY

Contact the Versalis sales office nearest to you regarding availability and your specific application requirements.

## FOOD CONTACT STATUS

Eraclene MQ 70 U BA complies with the rules and regulations of the European Union, as well as other countries, regarding the use of plastic materials in food contact applications. Certificates of compliance are available upon request.

## TECHNICAL MANAGEMENT POLYETHYLENE

### Center and South Europe and Americas

Versalis S.p.A.

Head Office

Piazza Boldrini, 1

20097 San Donato Milanese (MI) - Italy

tel. +39 0252032998 + 39 0252042262

tel. +39 0252042005 + 39 0252032072

+39 0252042984

Mantova

Via Taliercio 14 - 46100 Mantova (MN) - Italy

tel. +39 0376305520 / +39 0376305620

### North Europe and ROW

Versalis S.p.A.

4531 Route des Dunes - CS 20060 Mardyck 59279

Dunkerque - France

tel. +33 328235516 / +33 328235512

Duesselder Str. 13

65760 Eschborn - Deutschland

tel +49 15140260561

**IMPORTANT:** please consult the relevant safety data sheet for more detailed information. The information and data presented herein are to the best of our knowledge true and accurate but no warranty or guarantee, expressed or implied, is made nor is any liability accepted with respect to the use of such information and data. Versalis is available to provide the guaranteed values for each product on demand

**DISCLAIMER:** it is the sole responsibility of the end-user to determine the safety, the regulatory compliance as well as the technical suitability of the product for the intended application. The product is not intended for use in medical devices and pharmaceutical applications; Versalis declines all responsibility and cannot be held liable in case of use in the above-mentioned applications.