DATASHEET



ASTM Property

| Grade | XL610H | | | |
|--|---|--------------------------|-------|--|
| Product | LDPE | LDPE | | |
| | | | | |
| General Information | | | | |
| Key Features | XL610H resin is produced by ExxonMobil Chemical's autoclave process technology. XL610H resin is a product designed for high speed extrusion coating. | | | |
| Applications | - High speed extrusion coating and lamination | | | |
| Item | Measuring Method | Unit | Value | |
| Physical | | | | |
| Melt Flow Index | ASTM D1238 | g/10min | 7.8 | |
| Density | ASTM D1505 | g/cm³ | 0.919 | |
| Thermal | | | | |
| Melting Point | LC Method | °C | 107 | |
| VICAT Softening Temperature | ASTM D1525 | °C | 89 | |
| Processing Properties | | | | |
| Neck-in (constant output) - 150 m/min, 315℃ | LC Method | cm | 3.8 | |
| Maximum coating speed | LC Method | m/min | 500 | |
| Minimum coating weight (constant output, 315°C) | LC Method | g/m² | 9 | |
| Film Properties | | | | |
| Barrier - MVTR (90% RH, 37.8℃, 25µm) | ASTM F372 | g/m²/24hr | 18.5 | |
| Barrier - O2 GTR | ASTM F372 | 104 cm³(STP)µm/m²24h atm | 20 | |

1. Physical Properties : these are not to be construed as specifications

* The last update date : 2021/10/01