

## RIBLENE®

## FH 39 F

LDPE

Low density polyethylene

Riblene FH 39 F is a low density polyethylene (LDPE) suitable for blown film extrusion. Riblene FH 39 F is characterised by a good balance between processability and mechanical properties. Films manufactured by Riblene FH 39 F are easily heat shrinkable and have good optical and mechanical properties.

### Main Applications

Riblene FH 39 F is recommended for the extrusion of packaging film, for the production of hygienic and sanitary film and for blends.

### Main Properties

Resin Properties	Value	Unit	Test Method
Melt Flow Rate (190 °C/2,16 kg)	1,2	g/10min	ISO 1133
Melt Flow Rate (190 °C/5 kg)	-	g/10min	ISO 1133
Melt Flow Rate (190 °C/21,6 kg)	-	g/10min	ISO 1133
Density	0,924	g/cm <sup>3</sup>	ISO 1183
Melting Point	111	°C	Internal method
Brittleness temperature	< -75	°C	ASTM D 746
Vicat softening point (1 kg)	95	°C	ISO 306/A

Film Properties *	Value	Unit	Test Method
Tensile stress at yield MD	11	MPa	ISO 527-3
Tensile stress at yield TD	11	MPa	ISO 527-3
Tensile stress at break MD	24	MPa	ISO 527-3
Tensile stress at break TD	23	MPa	ISO 527-3
Elongation at break MD	400	%	ISO 527-3
Elongation at break TD	600	%	ISO 527-3
1% Secant modulus MD	180	MPa	ISO 527-3
1% Secant modulus TD	190	MPa	ISO 527-3
Elmendorf tear resistance MD	60	N/mm	ISO 6383-2
Elmendorf tear resistance TD	55	N/mm	ISO 6383-2
Impact resistance F50 (Dart Drop Test)	140	g	ISO 7765-1/A
Dynamic coefficient of friction (COF)	> 0,5	-	ISO 8295
Haze	5,5	%	ISO 14782
Gloss, 45°	71	%	ASTM D 2457
Recommended film thickness	30 ÷ 100	micron	-

(\* ) Typical value for a film extruded with BUR 1:3, thickness 40 µm. Actual properties are typical and may vary depending upon operating conditions and additive package.

## Processing notes

Riblene FH 39 F is easily processable using blown film technology. Melt temperature should be between 160 °C and 200 °C. Recommended thickness: 30 - 100 µm.

## Storage and Handling

Riblene FH 39 F is supplied in pellet form. This material may readily be conveyed and bulk fed through equipment designed for conventional pelletised polyethylene resin, provided the equipment is designed to prevent accumulation of the fines and dust particles that are contained in all polyethylene resins. These fines and dust particles can, under certain conditions, pose an explosion hazard. We recommend that the conveying system used be equipped with filters of adequate size, operated and maintained in such a manner to ensure that no leaks develop and earthed adequately. We further recommend that good housekeeping should be practised throughout your facility.

The product should be stored in dry conditions at temperatures below 50 °C and protected from sunlight. Improper storage can initiate degradation which results in odour generation, colour changes and can have negative effects on the physical properties of the product.

Before using this product it is recommended to read and understand the relevant Safety Data Sheet.

## Availability

Contact the Versalis sales office nearest to you regarding availability and your specific application requirements.

## Food Contact Status

Riblene FH 39 F complies with the rules and regulations of the European Union, as well as other countries, regarding the use of plastic materials in food contact applications. Certificates of compliance are available upon request.

## Technical Management Polyethylene

### Center and South Europe and Americas

Versalis S.p.A.

Head Office

Piazza Boldrini 1 - 20097 San Donato Milanese (MI) - Italy

tel. +39 0252032998 +39 0252042262

+39 0252042005 +39 0252032072

+39 0252042984

Mantova

Via Taliercio 14 - 46100 Mantova (MN) - Italy

tel. +39 0376305520 +39 0376305620

### North Europe and ROW

Versalis S.p.A.

4531 Route des Dunes - CS 20060 Mardyck

59279 Dunkerque - France

tel. +33 328235516 +33 328235512

Duesselder Str. 13 65760

Eschborn - Germany

tel. +49 15140260561

**IMPORTANT:** please consult the relevant safety data sheet for more detailed information. The information and data presented herein are to the best of our knowledge true and accurate but no warranty or guarantee, expressed or implied, is made nor is any liability accepted with respect to the use of such information and data. Versalis is available to provide the guaranteed values for each product on demand.

**DISCLAIMER:** it is the sole responsibility of the end-user to determine the safety, the regulatory compliance as well as the technical suitability of the product for the intended application. The product is not intended for use in medical devices and pharmaceutical applications; Versalis declines all responsibility and cannot be held liable in case of use in the above mentioned applications.