

TECHNICAL DATA SHEET

TECHNYL C 116S V35 BK 21N

(Previously DOMAMID 6LVG35 403 BK99)

Polyamide 6, 35% glass fiber reinforced, improved surface finish, for injection molding, black

General

Feature	Improved surface finish
Polymer type	PA6 (Polyamide 6)
Processing technology	Injection molding

Product identification

ISO 1043 abbreviation	PA6-GF35
ISO 16396 designation	PA6,GF35,M1,S12-110

	Condition	Standard	Unit	Value
Density		ISO 1183	g/cm ³	1.42

Physical properties

				dam / cond.*
Tensile modulus	1 mm/min	ISO 527-1/-2	MPa	11500 / 7300
Stress at break		ISO 527-1/-2	MPa	195 / 130
Strain at break		ISO 527-1/-2	%	3.2 / 6
Flexural modulus, ISO 178	2 mm/min	ISO 178	MPa	9000 / 7600
Flexural strength, ISO 178	2 mm/min	ISO 178	MPa	315 / 205
Charpy impact strength, +23°C	+23°C	ISO 179/1eU	kJ/m ²	95 / 100
Charpy notched impact strength, +23°C	+23°C	ISO 179/1eA	kJ/m ²	15 / 25

*: conditioned according to ISO 1110

Processing conditions

Drying temperature/time	75-85°C / 2-4h (with dew point of dried air < -30 °C)
Recommended melt temperature	250 - 290 °C
Recommended mould temperature	80 - 100 °C

Disclaimer

The information provided in this documentation corresponds to our technical knowledge at the date of its publication and do not constitute a specification. This information may be subject to revision at our discretion. Domo cannot anticipate all conditions under which this information and our products of other manufactures in combination with our products may be used. Domo accepts no responsibility for results obtained by the application of this information or for the safety and suitability of our products alone or in combination with other products. Users are advised to make their own tests to determine the safety and suitability of each product or product combination for their own purposes. Unless otherwise agreed in writing, Domo sells the product without warranties. Buyers and users assume all responsibility and liability for loss or damage arising from handling and use of our products, whether used alone or in combination with other products. Unless specifically indicated, the grades mentioned are not suitable for applications in the pharmaceutical/medical sector.