

TECHNICAL DATA SHEET

TECHNYL MAX A 219 XV65 NC
(Previously DOMAMID XS 66V65H1 119 NC)

Polyamide 66, 65% glass fiber reinforced, heat-aging stabilized, for injection moulding, natural color

General

Feature	Heat-aging stabilized	
Polymer type	PA66 (Polyamide 66)	
Processing technology	Injection molding	
Certification	RoHS	EC 1907/2006 (REACH)
Colors available	Black	Natural
Forms	Pellets	

Product identification

ISO 16396 designation	PA66,GF65,M1H,S14-250
-----------------------	-----------------------

Condition	Standard	Unit	Value
-----------	----------	------	-------

Physical properties

Condition	Standard	Unit	Value
Density	ISO 1183	g/cm ³	1.78
Molding shrinkage, parallel	ISO 294-4, 2577	%	0.1 - 0.3
Molding shrinkage, normal	ISO 294-4, 2577	%	0.3 - 0.45

Mechanical properties

dam / cond.*

Condition	Standard	Unit	Value	
Tensile modulus	1 mm/min	ISO 527-1/-2	MPa	25000 / 22500
Stress at break	5 mm/min	ISO 527-1/-2	MPa	250 / 220
Strain at break	5 mm/min	ISO 527-1/-2	%	2 / 2.3
Flexural modulus, ISO 178	2 mm/min	ISO 178	MPa	21300 / -
Flexural strength, ISO 178	2 mm/min	ISO 178	MPa	400 / -
Charpy impact strength, +23°C	+23°C	ISO 179/1eU	kJ/m ²	75 / -
Charpy impact strength, -30°C	-30°C	ISO 179/1eU	kJ/m ²	70 / -
Charpy notched impact strength, +23°C	+23°C	ISO 179/1eA	kJ/m ²	17 / -
Izod impact strength, +23°C	+23°C	ISO 180/1U	kJ/m ²	65 / -
Izod notched impact strength, +23°C	+23°C	ISO 180/1A	kJ/m ²	17 / -

TECHNICAL DATA SHEET

TECHNYL MAX A 219 XV65 NC

	Condition	Standard	Unit	Value
Thermal properties				
Melting temperature, 10°C/min		ISO 11357-1	°C	260
Temp. of deflection under load, 1.80 MPa	1.80 MPa	ISO 75	°C	245
Vicat softening temperature	50°C/h - 50N	ISO 306	°C	230


Electrical properties				
Volume resistivity		IEC 62631-3-1	ohm.m	10000000000

Burning behaviour				
Flammability, 0.75 mm	0.75 mm	UL 94		HB
Burning rate, FMVSS, Thickness 1 mm		FMVSS 302		< 100 mm/min

*Test run at 23°C if not differently specified, DAM state (dry as moulded), valid for natural colored products.
: conditioned according to ISO 1110

Processing conditions	
Drying temperature/time	75-85°C / 2-4h (with dew point of dried air < -30 °C)
Recommended melt temperature	280 - 305 °C
Recommended mould temperature	70 - 100 °C

These parameters are typical of the product but should be related to the type of machinery used and to the type of moulded part.



Disclaimer

The information provided in this documentation corresponds to our technical knowledge at the date of its publication and do not constitute a specification. This information may be subject to revision at our discretion. Domo cannot anticipate all conditions under which this information and our products of other manufactures in combination with our products may be used. Domo accepts no responsibility for results obtained by the application of this information or for the safety and suitability of our products alone or in combination with other products. Users are advised to make their own tests to determine the safety and suitability of each product or product combination for their own purposes. Unless otherwise agreed in writing, Domo sells the product without warranties. Buyers and users assume all responsibility and liability for loss or damage arising from handling and use of our products, whether used alone or in combination with other products. Unless specifically indicated, the grades mentioned are not suitable for applications in the pharmaceutical/medical sector.