

STYRENICS

Edistir® N 3380 Balance BA100

 GPPS
 GPPS bio-attributed


SUSTAINABILITY

Bio raw materials can be used in production processes together with traditional ones. To attribute the characteristics of sustainability to the final product, Versalis applies the **Mass Balance** approach, an acknowledged chain of custody that ensures the allocation of sustainability characteristics of raw materials, to final products in a regulated and verifiable manner.

Balance® BA products are provided with a **sustainability declaration** indicating the amount of Bio Attributed component. They guarantee identical performance, quality and properties, as they do not differ in chemical composition and physical-mechanical performance from standard products.

The production of Edistir® N3380 Balance BA100 contributes to the circular economy model since the bionafta comes from biological feedstock (eg. vegetable oils).

Balance® BA100 products have 100% of bio-attributed share.

PROPERTIES

General	Test Conditions	Test Method	Unit	Value
Water Absorption	24 h - 23°C	ISO 62	%	< 0,1
Density	-	ISO 1183	g/cm ³	1,05
Bulk density	-	ISO 60	g/cm ³	0,65
Rheological				
Melt Flow Index	200 °C - 5 kg	ISO 1133	g/10'	2
Mechanical				
Tensile stress at break	5 mm / min	ISO 527	MPa	49
Tensile strain at break	5 mm / min	ISO 527	%	2,5
Rockwell Hardness	L/M Scale	ISO 2039/2	-	M 80
Tensile Modulus	1 mm / min	ISO 527	MPa	3300
Flexural strenght	2 mm/min	ISO 178	MPa	91
Izod Impact Strenght, notched	+ 23 °C - 4 mm	ISO 180/1A	kJ/m ²	1,9
Izod Impact Strenght, notched	- 30 °C - 4 mm	ISO 180/1A	kJ/m ²	1,7
Thermal				
Coefficient of Linear Thermal Expansion	-	ASTM D 696	10 ⁻⁵ / °C	7
Thermal Conductivity	-	ISO 8302	W/(K·m)	0,17
Moulding Shrinkage	-	ISO 294/4	%	0,3 ÷ 0,6
Vicat Softening Temperature	10 N - 50 °C/h	ISO 306/A	°C	106
Vicat Softening Temperature	50 N - 50 °C/h	ISO 306/B	°C	101
Deflection temperature under load (annealed)	1,82 MPa - 120°C/h	ISO 75-2/A	°C	95
Flammability				
Flame Behaviour	1,5 mm	UL 94*	cl.	HB
Glow Wire Test (GWT)	3 mm	IEC 60695-2-10	°C	650

*internal test



EDISTIR® GPPS bio-attributed

N 3380 Balance BA100

APPLICATIONS

Edistir® N 3380 Balance BA100 is suitable for:

- Foamed packaging trays
- Clear panels for shower boxes
- Insulation boards XPS
- BOPS
- Clear moulded fridge components
- Medical items

PROCESSABILITY



Extrusion:

- Melt temperature 210°C - 240°C

Injection Moulding:

- Predrying normally not required
- Melt Temperature 220 -270°C
- Mould Temperature 20 - 60°C

STORAGE

-  Store away from atmospheric agents and direct sunlight, away from sources of heat and light.
-  The product, if stored correctly, keeps its characteristics for at least fifteen months.

AVAILABILITY

To find out about the availability of the resin and for information on specific applications, please contact the nearest Versalis sales office.

FOOD DECLARATION

Edistir® N 3380 Balance BA100 as supplied in the original packaging, by composition is compliant to some existing regulations on plastic materials intended for food contact.

TECHNICAL MANAGEMENT STYRENICS AND CLIENT RELATIONSHIP

For further information, please contact Versalis directly writing to info.styrenics@versalis.eni.com.

Versalis S.p.A.

Head Office
Piazza Boldrini, 1
20097 San Donato Milanese (MI) - Italy
tel. +39 02 52032087 / +39 02 52032190
tel. +39 02 52042005 / +39 02 52032319

Mantova
Via Taliercio 14 - 46100 Mantova (MN) - Italy
tel. +39 03 76305520 / +39 03 76305741

PLEASE NOTE: please consult the relevant safety data sheet for more detailed information. The information and data contained in this document are indications that do not constitute a guarantee if the buyer does not fulfill the obligations and requirements of the case. Versalis is available for any suggestions and further information.

DISCLAIMER: it is the responsibility of the end user to verify the safety, regulatory compliance and technical suitability of the product for the specific application.