

TECHNICAL DATA SHEET

TECHNYL A 218 BK 21N

TECHNYL A 218 BK 21N is an unreinforced polyamide 66, standard viscosity, heat stabilized for injection moulding. This grade offers all the primary properties of unreinforced polyamide 66. In addition, it has improved resistance to high temperature, and can be used for components which will withstand long-term temperature stresses.

General

| | | |
|-----------------------|--|-------------------------|
| Feature | Heat-aging stabilized | |
| Polymer type | PA66 (Polyamide 66) | |
| Processing technology | Injection molding | |
| Certification | RoHS EC 1907/2006 (REACH) | UL-Yellow Card |
| Applications | Consumer good application General Purpose | Industrial Applications |
| Colors available | Black | Natural |
| Forms | Pellets | |

Product identification

| | |
|-----------------------|------|
| ISO 1043 abbreviation | PA66 |
|-----------------------|------|

Physical properties

| | Condition | Standard | Unit | Value |
|------------------------------|----------------|-----------------|-------------------|---------|
| Density | | ISO 1183 | g/cm ³ | 1.14 |
| Humidity absorption | T=23°C, 50% RH | ISO 62 | % | 3 - 3.1 |
| Water absorption | 24 hr, 23°C | ISO 62 | % | 1.3 |
| Water absorption, saturation | | | % | 8.3 |
| Molding shrinkage, parallel | | ISO 294-4, 2577 | % | 1.6 |
| Molding shrinkage, normal | | ISO 294-4, 2577 | % | 1.5 |

| | Condition | Standard | Unit | Value |
|---------------------------------------|-----------|--------------|-------------------|---------------------|
| Mechanical properties | | | | dam / cond.* |
| Tensile modulus | 1 mm/min | ISO 527-1/-2 | MPa | 3300 / 1300 |
| Stress at break | | ISO 527-1/-2 | MPa | 55 / 50 |
| Strain at break | | ISO 527-1/-2 | % | 20 / 150 |
| Flexural modulus, ISO 178 | 2 mm/min | ISO 178 | MPa | 3000 / 1300 |
| Flexural modulus, ASTM D790 | 2 mm/min | ASTM D790 | MPa | 3300 / - |
| Flexural strength, ISO 178 | 2 mm/min | ISO 178 | MPa | 120 / 70 |
| Flexural strength, ASTM D790 | 2 mm/min | ASTM D790 | MPa | 125 / - |
| Charpy notched impact strength, +23°C | +23°C | ISO 179/1eA | kJ/m ² | 4.5 / 10 |
| Izod notched impact strength, +23°C | +23°C | ISO 180/1A | kJ/m ² | 4 / 10 |


Thermal properties

| | | | | |
|--|----------|-------------|----|-----|
| Melting temperature, 10°C/min | | ISO 11357-1 | °C | 263 |
| Temp. of deflection under load, 0.45 MPa | 0.45 MPa | ISO 75 | °C | 200 |
| Temp. of deflection under load, 1.80 MPa | 1.80 MPa | ISO 75 | °C | 82 |

Electrical properties

| | | | | |
|--------------------------------|------------|---------------|-------|--------|
| Volume resistivity | | IEC 62631-3-1 | ohm.m | 1E+013 |
| Surface resistivity | | IEC 62631-3-1 | ohm | 1E+015 |
| Comparative tracking index | Solution A | IEC 60112 | V | 600 |
| CTI performance level category | | Sol A | | PLC 0 |
| Dielectric strength | 1 mm | IEC 60243-1 | kV/mm | 22 |

Burning behaviour


| | | | | |
|---|--|----------------|----|-----|
| UL Yellow Card availability  | Click here to have access to the UL Yellow Card → QMFZ2.E44716 | | | |
| Flammability, 1.5 mm | 1.5 mm | UL 94 | | V2 |
| Flammability, 3.0 mm | 3.0 mm | UL 94 | | V2 |
| Glow-wire flammability index, GWFI, 1.5 mm | 1.5 mm | IEC 60695-2-12 | °C | 650 |

*: conditioned according to ISO 1110

Processing conditions


| | |
|-------------------------------|--------------|
| Drying temperature/time | 80 °C |
| Suggested max moisture | 0.2 % |
| Rear temperature | 265 - 275 °C |
| Middle temperature | 270 - 280 °C |
| Front temperature | 280 - 285 °C |
| Recommended mould temperature | 60 - 80 °C |

Stress-strain, dry



| Temperature (°C) | |
|------------------|------------|
| 1 | Spannung 1 |
| 2 | Spannung 2 |
| 3 | Spannung 3 |
| 4 | Spannung 4 |

Stress-strain, conditioned



| Temperature (°C) | |
|------------------|------------|
| 1 | Spannung 1 |

Injection notes

The material is supplied in airtight bags, ready for use. In case that the virgin material has absorbed moisture, it must be dried with a dehumidified air drying equipment, dew point minimum -20°C. Recommended time 2-4h.

Injection advice

For unfilled polyamides, Domo recommends the use of high alloy steel with a low chromium content. For example: X38CrMoV5-1 (EN Norm) - 1.2367 /1.2343 (DIN Norm). In the case of high requirements on surface quality a mould temperature of up to 120°C can be considered. The processing parameters like processing temperatures are a recommendation and can be adjusted in function of injection machine size, part geometry / design.

Disclaimer

The information provided in this documentation corresponds to our technical knowledge at the date of its publication and do not constitute a specification. This information may be subject to revision at our discretion. Domo cannot anticipate all conditions under which this information and our products of other manufactures in combination with our products may be used. Domo accepts no responsibility for results obtained by the application of this information or for the safety and suitability of our products alone or in combination with other products. Users are advised to make their own tests to determine the safety and suitability of each product or product combination for their own purposes. Unless otherwise agreed in writing, Domo sells the product without warranties. Buyers and users assume all responsibility and liability for loss or damage arising from handling and use of our products, whether used alone or in combination with other products. Unless specifically indicated, the grades mentioned are not suitable for applications in the pharmaceutical/medical sector.