TECHNICAL DATASHEET

POLYPROPYLENE TATREN IM 65 73

Impact copolymer for injection moulding

DESCRIPTION

TATREN IM 65 73 is a controlled rheology impact copolymer of good processing stability and high fluidity. This grade contains nucleating and antistatic agent.

TATREN IM 65 73 is characterised by high stiffness, good impact resistance and good flow.

APPLICATIONS

TATREN IM 65 73 is intended especially for high speed thin wall injection moulding of products where good impact resistance is required. Typical end products are different household and garden articles like bowls, pails, storage boxes, trays, caps, closures, boxes for food packaging, toys etc. This grade can be used in mixtures with TATREN homopolymer grades.

TATREN IM 65 73 is well suited for LFT technology to produce sound insulation car parts by compression moulding. This grade can be used for compounding as well.

PRODUCT COMPLIANCE

See DDS.

PROPERTIES*

Parameter	Note	Test method	Unit	Typical value
MFR - Melt Mass-Flow Rate (230°C, 2.16 kg)	-	ISO 1133-1	g/10 min	65
Tensile Stress at Yield	2	ISO 527-1,2	MPa	22.5
Tensile Strain at Yield	2	ISO 527-1,2	%	4.5
Modulus of Elasticity in Tension	2	ISO 527-1,2	MPa	1300
Flexural Modulus	2	ISO 178	MPa	1250
Izod Impact Strength (notched, 23°C)	2	ISO 180/A	kJ/m²	8.5
Izod Impact Strength (notched, -20°C)	2	ISO 180/A	kJ/m²	4.5
Hardness - Rockwell	2	ISO 2039-2	R scale	80
HDT (0.45 MPa, flatwise)	2	ISO 75-1,2	°C	85
Recommended Processing Temperature	-	-	°C	190 - 250

PROCESSING

TATREN IM 65 73 can be processed on standard injection moulding machines.



^{*}Typical properties, not to be used as specification.

⁽²⁾ Typical properties measured on standard injection moulded test specimen according to ISO 294-1.

TECHNICAL DATASHEET

POLYPROPYLENE TATREN IM 65 73

Impact copolymer for injection moulding

STORAGE AND HANDLING

Pellets are packed in 25 kg polyethylene bags and transported on shrink-wrapped or stretch-wrapped pallets at eligible load of polymer 1375 kg. Heat treated pallets are provided by PRS, a member of the Faber Halbertma Group, operating a pooling system which collects the pallets after use, and organizes reuse as part of a sustainable, circular system. PRS pallets remain property of PRS at all times. Transportation in road silo or rail silo is also available. For more detailed information please contact a sales representative at SLOVNAFT or at MOL Petrochemicals.

Since polypropylene is a combustible substance, the fire safety rules applicable for combustible materials in warehouses and store rooms should be observed.

If polymer is stored in conditions of high humidity and fluctuating temperatures, then atmospheric moisture can condense inside the packing. If it happened, it is recommended the pellets to be dried before use. During the storage polypropylene should not be exposed to UV radiation and temperatures above 40°C. Producer does not take responsibility for any damages caused by adverse storage.

REACH STATEMENT

Polymers are exempt of REACH registration. However, their raw materials which mean monomers and relevant additives have been registered. SLOVNAFT, a.s. is committed to fully respect legislation and will only use REACH compliant raw materials. At this point in time PP TATREN does not contain any substances specifically identified as SVHC at levels greater than 0.1%.

RECYCLING

Polypropylene resins are suitable for recycling using modern recycling methods. In-house production waste should be kept clean to facilitate direct recycling.

SAFETY

See MSDS.



TECHNICAL DATASHEET

POLYPROPYLENE TATREN IM 65 73

Impact copolymer for injection moulding

MANUFACTURER

SLOVNAFT, a.s. Vlčie hrdlo 1 824 12 Bratislava Slovak Republic

E-mail: infopolymer@slovnaft.sk

TECHNICAL SUPPORT

POLYMER APPLICATIONS ENGINEERING SLOVNAFT, a.s. Vlčie hrdlo 1 824 12 Bratislava Slovak Republic Telephone:

E-mail: polymerservice@slovnaft.sk

+ 421 2 5859 7250

SALES OFFICES

H-3581 Tiszaújváros,

Fax: +36 1 8877 647

P.O. Box: 20, Hungary

Mobile: + 36 30 447 4441

HUNGARY

GERMANY

Im Trutz Frankfurt 49, D-60322 Frankfurt am Main, Germany Telephone: +49 69 154 04 0 Fax: +49 69 154 04 41

E-mail:

polymersales@molgermany.de

ITALY

Via Montefeltro, 4 20156 Milano, Italy

Telephone: +39 02 58 30 5523

Fax: +39 02 58 30 3492

E-mail: molitalia@molgroupitaly.it

AUSTRIA

Walcherstrasse 11A, 7.Stock A-1020 Wien, Austria Mobile: +43 664 96 33 578 E-mail:

Katalin Horvath@molaustria.at

FRANCE

Paris, France

Mobile: +33 7 89 86 10 64

E-mail: iren.husson@molgroupitaly.it

POLAND

UI.Postępu 17D 02-676 Warszawa, Poland Telephone: +48 22 545 70 70 Fax: +48 22 545 70 60 E-mail: petchem@slovnaft.pl

ROMANIA

Str.Daniel Danielopolu 4-6 ET1 Sector 1 Cod 014 134 Bucuresti, Romania Telephone: +40 21 204 85 00 +40 21 204 85 02 Fax: +40 21 232 10 59

E-mail: petchem@molromania.ro

UKRAINE

04053 Kiev

Sichovykh Striltsiv str. 50, 5th floor, office

5-B, Ukraine

Tel.: +380 44 374 00 80 | +380 67 463

58 69

Fax: +380 44 374 00 90

E-mail: Jzavojko@mol-ukraine.com.ua

CROATIA, SLOVENIA, SERBIA, MONTENEGRO, BOSNIA AND HERZEGOVINA, NORTH MACEFDONIA, ALBANIA, KOSOVO

Zadarska 80 HR-10000 Zagreb, Croatia Telephone: +385 1 6160 637

Fax: +385 1 6160 601

E-mail: polymersales@tifon.hr

OTHER EUROPEAN COUNTRIES

Telephone: +36 20 456 1889 +36 70 373 9209

E-mail: polymersales@mol.hu

E-mail: polymersales@mol.hu

SLOVAKIA AND CZECH REPUBLIC

Vlčie hrdlo 1 824 12 Bratislava, Slovak Republic Telephone:

+421 2 5859 5426

+421 2 5859 5431

+421 2 5859 5429

+421 2 5859 5428

E-mail: predajpolymerov@slovnaft.sk

DISCLAIMER

©2022 MOL Group. To the extent the user is entitled to disclose and distribute this document, the user may forward, distribute, and/or photocopy this copyrighted document only if unaltered and complete, including all of its headers, footers, disclaimers, and other information. You may not copy this document to a web site. MOL Group does not guarantee the typical (or other) values. Analysis may be performed on representative samples and not the actual product shipped. The information in this document relates only to the named product or materials when not in combination with any other product or materials. We based the information on data believed to be reliable on the date compiled, but we do not represent, warrant, or otherwise guarantee, expressly or impliedly, the merchantability, fitness for a particular purpose, suitability, accuracy, reliability, or completeness of this information or the products, materials, or processes described. The user is solely responsible for all determinations regarding any use of material or product and any process in its territories of interest. We expressly disclaim liability for any loss, damage, or injury directly or indirectly suffered or incurred as a result of or related to anyone using or relying on any of the information in this document. There is no endorsement of any product or process, and we expressly disclaim any contrary implication. The terms, "we", "our", "MOL", or "MOL Group" are used for convenience, and may include any one or more of MOL Group, or any affiliates they directly or indirectly control. MOL Group, the MOL Group logo, and all other product names used herein are trademarks of MOL Plc. or SLOVNAFT, a.s. unless indicated otherwise.

