

TECHNICAL DATA SHEET

**TECHNYL SHAPE C 448CR BK**  
(Previously DOMAMID 6HVI4H2HR2 BK)

Polyamide 6, heat-aging stabilized, hydrolisis stabilized, impact modified, high viscosity, for extrusion of pipes, black

**General**

Feature	Heat-aging stabilized Impact modified	High viscosity
Polymer type	PA6 (Polyamide 6)	
Processing technology	Extrusion	
Certification	RoHS	

**Product identification**

ISO 1043 abbreviation	PA6-I
ISO 16396 designation	PA6-I,E1HW,S14-020

Condition	Standard	Unit	Value
-----------	----------	------	-------

**Physical properties**

Density		ISO 1183	g/cm <sup>3</sup>	1.07
Melt volume-flow rate, MVR, 5.0 kg	275°C, 5kg	ISO 1133	cm <sup>3</sup> /10 min	3

**Mechanical properties**

dam / cond.\*

Tensile modulus	1 mm/min	ISO 527-1/-2	MPa	1900 / 600
Stress at break	5 mm/min	ISO 527-1/-2	MPa	50 / 50
Strain at break	5 mm/min	ISO 527-1/-2	%	> 50 / > 200
Flexural modulus, ISO 178	2 mm/min	ISO 178	MPa	1800 / 450
Charpy impact strength, +23°C	+23°C	ISO 179/1eU		NB / NB
Charpy notched impact strength, +23°C	+23°C	ISO 179/1eA	kJ/m <sup>2</sup>	85 / 100

**Thermal properties**


Melting temperature, 10°C/min		ISO 11357-1	°C	221
-------------------------------	--	-------------	----	-----

Test run at 23°C if not differently specified, DAM state (dry as moulded).  
\*: conditioned according to ISO 1110

**Processing conditions**

Drying temperature/time 75-85°C / 2-4h (with dew point of dried air < -30 °C)

*These parameters are typical of the product but should be related to the type of machinery used and to the type of moulded part.*



**Disclaimer**

The information provided in this documentation corresponds to our technical knowledge at the date of its publication and do not constitute a specification. This information may be subject to revision at our discretion. Domo cannot anticipate all conditions under which this information and our products of other manufactures in combination with our products may be used. Domo accepts no responsibility for results obtained by the application of this information or for the safety and suitability of our products alone or in combination with other products. Users are advised to make their own tests to determine the safety and suitability of each product or product combination for their own purposes. Unless otherwise agreed in writing, Domo sells the product without warranties. Buyers and users assume all responsibility and liability for loss or damage arising from handling and use of our products, whether used alone or in combination with other products. Unless specifically indicated, the grades mentioned are not suitable for applications in the pharmaceutical/medical sector.