

F 722

ABS Resin

Provisional data sheet

Versalis Sinkral® F 722 is an ABS with very high impact properties dedicated to injection moulding: it is specifically designed for applications that require the high processing flowability together with an excellent impact and mechanical performance in use.

Applications

Versalis Sinkral® F 722 is suitable for:

- luggage
- tool boxes.

Typical processing data

Injection moulding:

- dry for 2 ÷ 4h at 80°C
- melt temperature: 190°C ÷ 220°C

Certification

Storage

- ⚠ Store away from atmospheric agents and direct sunlight, away from sources of heat and light.
- 🕒 The product, if stored correctly, keeps its characteristics for at least fifteen months.

General information

Sinkral® F 722 is available in natural colour.

For further information, please contact Versalis directly writing to info.styrenics@versalis.eni.com.

F 722

ABS Resin

Provisional data sheet

Property	Test Conditions	Test method	Units	Values
General				
Water absorption	24h - 23°C	ISO 62	%	0,3
Density	-	ISO 1183	g/cm ³	1,04
Rheological				
Melt flow rate	220°C - 10kg	ISO 1133	g/10'	14
Mechanical				
Tensile strain at break	50 mm/min	ISO 527	%	42
Strain at yield	50 mm / min	ISO 527	%	1,7
Tensile stress at yield	50 mm/min	ISO 527	MPa	39
Tensile modulus	1 mm/min	ISO 527	MPa	2400
Izod impact strength, notched	-30°C - 4mm	ISO 180/1A	kJ/m ²	11
Izod impact strength, notched	+23°C - 4mm	ISO 180/1A	kJ/m ²	29
Thermal				
Coefficient of linear thermal expansion	-	ISO 11359-2	10 ⁻⁵ /°C	9
Thermal conductivity	-	ASTM C 177	W/(K.m)	0,17
Moulding shrinkage	-	ISO 294/4	%	0,4 ÷ 0,6
Vicat softening temperature	50 N - 50°C/h	ISO 306/B	°C	99
Electrical				
Dielectric constant (relative permittivity)	1000 Hz secco/dry	IEC 60250	-	3,1
Dissipation factor	1000 Hz secco/dry	IEC 60250	-	15·10E-3
Surface resistivity	secco / dry	IEC 60093	ohm	10E14
Volume resistivity	secco / dry	IEC 60093	ohm·cm	10E15
Dielectric strength	secco / dry	IEC 60243	kV/mm	30

Please consult the relevant safety data sheet for more detailed information.

The information and data presented herein are to the best of our knowledge true and accurate but no warranty or guarantee, expressed or implied, is made nor is any liability accepted.

Versalis is available to provide the guaranteed values for each product on demand.