

TECHNICAL DATA SHEET

TECHNYL STAR S 60X1 V30 GY R7035 CF

TECHNYL STAR S 60X1 V30 GY R7035 CF is a grade based on a non-halogenated flame retardant system and on a patented high flow polyamide 6 resin (TechnylStar), reinforced of 30% of glass fiber, heat stabilized, for injection moulding. This grade is heat stabilized and provides optimized injection moulding performance.

General

Feature	Halogen and red phosphorus free flame retardant Very high flow Excellent surface finish	Arc resistant Corrosion resistant Low temperature impact resistant
Polymer type	PA6 (Polyamide 6)	
Processing technology	Injection molding	
Certification	UL-Yellow Card European Railways Certifications EN 45545-2	EC 1907/2006 (REACH)
Applications	Connectors	Electrical/Electronic Applications
Colors available	Black Grey	Natural
Forms	Pellets	

Product identification

ISO 1043 abbreviation	PA6-GF30 FR(40)
-----------------------	-----------------

Condition	Standard	Unit	Value
-----------	----------	------	-------

Physical properties

	Condition	Standard	Unit	Value
Density		ISO 1183	g/cm ³	1.42
Water absorption	24 hr, 23°C	ISO 62	%	0.9
Water absorption, saturation			%	4.1
Molding shrinkage, parallel		ISO 294-4, 2577	%	0.25
Molding shrinkage, normal		ISO 294-4, 2577	%	0.9

TECHNICAL DATA SHEET

TECHNYL STAR S 60X1 V30 GY R7035 CF

	Condition	Standard	Unit	Value
Mechanical properties				dam / cond.*
Tensile modulus	1 mm/min	ISO 527-1/-2	MPa	10000 / 6400
Stress at break		ISO 527-1/-2	MPa	110 / 70
Strain at break		ISO 527-1/-2	%	1.9 / 3.5
Flexural modulus, ISO 178	2 mm/min	ISO 178	MPa	9000 / 5000
Flexural modulus, ASTM D790	2 mm/min	ASTM D790	MPa	9670 / -
Flexural strength, ISO 178	2 mm/min	ISO 178	MPa	170 / 120
Flexural strength, ASTM D790	2 mm/min	ASTM D790	MPa	160 / -
Charpy impact strength, +23°C	+23°C	ISO 179/1eU	kJ/m ²	32 / 35
Charpy impact strength, -30°C	-30°C	ISO 179/1eU	kJ/m ²	25 / -
Charpy notched impact strength, +23°C	+23°C	ISO 179/1eA	kJ/m ²	5 / 6.5
Charpy notched impact strength, -30°C	-30°C	ISO 179/1eA	kJ/m ²	5 / -
Izod impact strength, +23°C	+23°C	ISO 180/1U	kJ/m ²	27 / 32
Izod notched impact strength, +23°C	+23°C	ISO 180/1A	kJ/m ²	5 / 6

Thermal properties


Melting temperature, 10°C/min		ISO 11357-1	°C	222
Temp. of deflection under load, 1.80 MPa	1.80 MPa	ISO 75	°C	205

Electrical properties

Volume resistivity		IEC 62631-3-1	ohm.m	1E+013
Surface resistivity		IEC 62631-3-1	ohm	6E+014
Comparative tracking index	Solution A	IEC 60112	V	600
CTI performance level category		Sol A		PLC 0
Dielectric strength	1 mm	IEC 60243-1	kV/mm	25

TECHNICAL DATA SHEET

TECHNYL STAR S 60X1 V30 GY R7035 CF

	Condition	Standard	Unit	Value
Burning behaviour				
UL Yellow Card availability 	Click here to have access to the UL Yellow Card → QMFZ2.E44716			
Flammability, 0.75 mm	0.75 mm	UL 94		V0
Flammability, 1.5 mm	1.5 mm	UL 94		V0
Flammability, 3.0 mm	3.0 mm	UL 94		V0
Glow-wire flammability index, GWFI, 0.75 mm	0.75 mm	IEC 60695-2-12	°C	960
Glow-wire flammability index, GWFI, 1.5 mm	1.5 mm	IEC 60695-2-12	°C	960
Glow-wire flammability index, GWFI, 3.0 mm	3.0 mm	IEC 60695-2-12	°C	960
Glow-wire ignition temperature, GWIT, 0.75 mm	0.75 mm	IEC 60695-2-13	°C	775
Glow-wire ignition temperature, GWIT, 1.5 mm	1.5 mm	IEC 60695-2-13	°C	800
Glow-wire ignition temperature, GWIT, 3.0 mm	3.0 mm	IEC 60695-2-13	°C	825
Oxygen index			%	35

*: conditioned according to ISO 1110

Processing conditions

Drying temperature/time	80 °C
Suggested max moisture	0.1 %
Rear temperature	240 - 245 °C
Middle temperature	245 - 255 °C
Front temperature	255 - 260 °C
Recommended mould temperature	60 - 90 °C

Injection notes

The material is supplied in airtight bags, ready for use. In case that the virgin material has absorbed moisture, it must be dried with a dehumidified air drying equipment, dew point minimum -20°C. Recommended time 2-4h.

Injection advice

All reinforced, flame retardant compounds generate some level of abrasion/corrosion to the steel processing equipment. These issues may be magnified by using incorrect processing conditions (temperatures, residence time, moisture level ...) during the moulding process. Therefore, Domo recommends you adhere to the processing conditions detailed in this technical data sheet. For equipment that comes into contact with molten flame retardant compounds, Domo advises you to use a steel with high chromium and high carbon content (having a minimum concentration of 16% chromium) to prevent corrosion and abrasion. For the correct reference of steel associated to flame retardant compounds' processing, please refer to your equipment manufacturers. In the case of high requirements on surface quality a mould temperature of up to 120°C can be considered. The processing parameters like processing temperatures are a recommendation and can be adjusted in function of injection machine size, part geometry / design.

Disclaimer

The information provided in this documentation corresponds to our technical knowledge at the date of its publication and do not constitute a specification. This information may be subject to revision at our discretion. Domo cannot anticipate all conditions under which this information and our products of other manufactures in combination with our products may be used. Domo accepts no responsibility for results obtained by the application of this information or for the safety and suitability of our products alone or in combination with other products. Users are advised to make their own tests to determine the safety and suitability of each product or product combination for their own purposes. Unless otherwise agreed in writing, Domo sells the product without warranties. Buyers and users assume all responsibility and liability for loss or damage arising from handling and use of our products, whether used alone or in combination with other products. Unless specifically indicated, the grades mentioned are not suitable for applications in the pharmaceutical/medical sector.